


This listing of claims will replace all prior versions, and listings of claims in the application:

Listing of Claims:

Claims 1-6. (Cancelled)

Claim 7. (Currently Amended) A polyurethane composition which cross-links via silane polycondensation and comprises

- A) at least one alkoxy silane-functional polyurethane having end groups corresponding to formula (I)




wherein

R¹ represents an organic group having 1 to 12 carbon atoms,

n is an integer from 2 to 4 and

X, Y, Z represent identical or different organic groups, provided that at least one of the groups is an alkoxy group having 1 to 4 carbon atoms,

- B) at least one filler,
C) at least one reaction product of
i) at least one aminosilane corresponding to formula (II)



wherein

R² represents a hydrogen atom or an aminoethyl group

n is 3 and

X, Y, Z have the meanings set forth for formula (I),

with

ii) at least one maleic or fumaric ester corresponding to formula (III)




wherein

[[R₃]] R³ represents an alkyl group having 1 to 12 carbon atoms, and


D) at least one organometallic compound.

Claim 8. (Currently Amended) The polyurethane composition of Claim 7 wherein [[R₁]] R¹ represents a group corresponding to formula (IIb)



wherein [[R₄]] R⁴ denotes an alkyl group having 1 to 4 carbon atoms.

Claim 9. (Currently Amended) The polyurethane composition of Claim 7 wherein component C) comprises an aminosilane compound corresponding to formula (V)



wherein

[[R₃]] R³ represents a linear or branched aliphatic hydrocarbon group having at most 12 carbon atoms,

n is 3 and

X, Y and Z represent methoxy or ethoxy groups.

Claim 10. (Previously Presented) The polyurethane composition of Claim 7 wherein X, Y and Z each represent a methoxy or ethoxy group.

Claim 11. (Previously Presented) The polyurethane composition of Claim 8 wherein X, Y and Z each represent a methoxy or ethoxy group.

Claim 12. (Previously Presented) The polyurethane composition of Claim 9 wherein X, Y and Z each represent a methoxy or ethoxy group.

Claim 13. (Previously Presented) The polyurethane composition of Claim 7 wherein X, Y and Z each represent a methoxy group in component A).


Claim 14. (Previously Presented) The polyurethane composition of Claim 8 wherein X, Y and Z each represent a methoxy group in component A).

Claim 15. (Previously Presented) The polyurethane composition of Claim 9 wherein X, Y and Z each represent a methoxy group in component A).

Claim 16. (Currently Amended) A process for the preparation of the polyurethane composition of Claim [[1]] Z which comprises mixing components A), B), and [[E]] D) with exclusion of moisture and subsequently adding component C, the reaction product of i) and ii).


Claim 17. (Currently Amended) A polyurethane composition which cross-links via silane polycondensation and comprises


- A) at least one alkoxy silane-functional polyurethane having end groups corresponding to formula (I)



wherein

R¹ represents a group corresponding to formula (IIb)





(IIb),

wherein $[[R_4]]$ R^4 represents an ethyl group.


n is 3 and

X, Y, Z represent methoxy or ethoxy groups,

B) at least one filler,

C) at least one reaction product of

i) at least one aminosilane corresponding to formula (II)



wherein

R^2 represents an aminoethyl group and

n, X, Y, Z have the meanings set forth for formula (I),

with

ii) at least one maleic or fumaric ester corresponding to formula (III)



wherein

$[[R_3]]$ R^3 represents an alkyl group having 1 to 12 carbon atoms,

and

D) at least one organometallic compound.